

TECHNICAL DATA

AREXPAN	DOSIFICACIÓN				CONCRETE DENSITY	THERMAL CONDUCTIVITY	COMPRESSIVE STRENGTH	RETRACTIÓN 28 DAYS
	DENSITY	AREXPAN	CEMENT 42,5R	SAND				
	Kg/m ³	litres	Kg	Kg	Kg/m ³	Kcal/hm°C	Kp/cm ²	mm
3-10 mm	350	1.100	150	-	600	0,12	30	0,018
8-18 mm	300	1.100	150	-	500	0,10	25	0,06
3-10 mm	350	1.100	300	300	1.000	0,19	125	0,07
0-6 mm	500	1.100	200	-	700	0,14	60	0,15